PATENT ABSTRACTS OF JAPAN

(11)Publication number:

64-015755

(43)Date of publication of application: 19.01.1989

(51)Int.CI.

G03G 9/08 C08L 67/00

(21)Application number : **62-171811**

(71)Applicant: MITSUBISHI RAYON CO LTD

(22)Date of filing:

09.07.1987

(72)Inventor: TAJIRI TAKAYUKI

ІТО КОІСНІ

IWASAKI HITOSHI

(54) PRODUCTION OF RESIN FOR TONER

(57)Abstract:

PURPOSE: To enhance low-temperature fixability, and resistances to offset and blocking by mixing a specified cross-linked polyester with a specified straight- chain polyester at a

specified temperature.

CONSTITUTION: The resin to be used for the toner is produced by mixing 100pts. wt. of the cross-linked polyester (A) having a glass transition point of $\geq 50^{\circ}$ C and a softening point of $\geq 200^{\circ}$ C with 0.5W80pts.wt. of the straight chain polyester (B) having a softening point of $\leq 150^{\circ}$ C and a weight average molecular weight of 3,000W50,000 at a temperature of said softening point of the polyester (B) W230° C. It is preferred that a polycondensate of a mixture of terephthalic acid and isophthalic acid, and ethylene glycol is used for the polyester (B), and a polycondensate of a mixture of trimellitic acid, terephthalic acid, and isophthalic acid, and ethylene glycol and/or aromatic diol, or the like is used for the polyester (A).

LEGAL STATUS

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]

Copyright (C): 1998,2000 Japanese Patent Office